

# 貼ってはがせるクラックスケール「Hurry(ハリー)」貼付回数試験

日時：2016.8.3（水曜日）

天気：晴れ

気温：33℃

湿度：75%

風向：北北東

風速：4m/s

○新品の貼付試験



貼付開始 16:30



貼付 1 回目  
16:31



貼付 5 回目  
16:33



貼付 10 回目  
16:35



貼付 15 回目  
16:37



貼付 20 回目  
16:41



貼付 25 回目  
16:43



貼付 30 回目  
16:46



貼付 35 回目  
16:48



貼付 40 回目  
16:50



貼付 45 回目  
16:51



貼付 50 回目  
16:52



貼付 55 回目  
16:54



貼付 60 回目  
16:56



貼付 62 回目  
16:57(貼付限界)

# 貼ってはがせるクラックスケール「Hurry(ハリー)」貼付回数試験

日時：2016.8.3（水曜日）

天気：晴れ

気温：33℃

湿度：75%

風向：北北東

風速：4m/s

○2 回目の貼付試験



洗剤で洗浄

16:59



水洗い

16:59



粘着力回復

17:02(3分)



貼付 1 回目

17:03



貼付 5 回目

17:04



貼付 10 回目

17:06



貼付 15 回目

17:08



貼付 17 回目

17:08(貼付限界)

# 貼ってはがせるクラックスケール「Hurry(ハリー)」貼付回数試験

日時：2016.8.3（水曜日）

天気：晴れ

気温：33℃

湿度：75%

風向：北北東

風速：4m/s

○3回目の貼付試験



洗剤で洗浄

17:10



水洗い

17:10



粘着力回復

17:13(3分)




貼付 1 回目

17:13



貼付 5 回目

17:14



貼付 10 回目

17:16




貼付 15 回目

17:17



貼付 20 回目

17:18



貼付 25 回目

17:20




貼付 30 回目

17:21



貼付 32 回目

17:22(貼付限界)



洗剤で洗浄  
17:24



乾燥  
17:24



粘着力回復  
17:27(3分)